

## QuestMark 1320

### High Performance Urethane (Semi-Gloss)

#### Directions for Use:

- *A suitable primer should be used before applying. Suitable primers include 1015, 1144, 1154.*
- *For 1-2 coat system, we recommend either a mechanical scarification or acid etching.*
- *For higher build, we recommend a fine brush blast.*
- *Ensure all dirt, oil, dust, or other debris has been removed and surface is dry.*
- *Mixing ratio is two parts A to one part B by volume. Standard kits are pre-measured for proper mixing.*
- *Mix thoroughly with slow-speed mixer until material is streak-free.*
- *Apply using a roller or brush.*
- *For cleanup, ketone solvents.*

**PLEASE NOTE: This product has a usable application time of 3-5 hours once mixed.**