



QuestMark 1357

Moisture Cured Urethane

Directions for Use:

- *A suitable primer should be used before applying. Recommended primer 1144 (clear).*
- *For 1-2 coat system, we recommend either a mechanical scarification or acid etching.*
- *For higher build, we recommend a fine brush blast.*
- *Ensure all dirt, oil, dust, or other debris has been removed and surface is dry.*
- *Stir well before using.*
- *Apply using a roller or brush.*
- *For cleanup, ketone solvents.*

PLEASE NOTE: This product has a usable application time of 3-5 hours once mixed.